MultiPanel - Armawall Sand High Profile with Armawall Armashield Matt

MP01

Job Details

Client

Reference No.

Project

Date

Specifications

Substrate: MultiPanel

New/Repaint: Texture New | Quality:

Interior/Exterior: Texture

Surface Preparation

Enure that the MultiPanel board's are securely fixed in accordance with manufacturer's specifications.The surface should be clean, dry and free from all dirt, dust, grease, oil mould and any other surface contamination that may affect adhesion. There must be less than 15% Wood Moisture Equivalent (WME) in the substrate before and during application. Please refer to the specific Armawall Product Data Sheets for further information and to ensure optimum coating system performance.

1st coat: Armawall Primer (D0225)

Application: Brush, Roller | Spreading Rate sqm/litre: 16

Reducer/Washup: Water | Recoat Time: 2

Dry Film Thickness : 0

2nd coat: Armawall Sand (D0228)

Application: Black Texture Roller | Spreading Rate sqm/litre: 2

Reducer/Washup: Water | Recoat Time: 4

Dry Film Thickness : 0

3rd coat: Armawall Armashield Matt (D0246)

Application: Nap Roller | Spreading Rate sqm/litre: 8

Reducer/Washup: Water | Recoat Time: 4

Dry Film Thickness : 0

DISCLAIMER

The technical information and suggestions for use and application presented herein represent the best information available to use and are believed to be reliable. They should not, however, be construed as controlling suggestions and there is no warranty of performance of our materials either expressed or implied. We urge that users of our materials conduct confirmatory tests to determine that final suitability for their specific end users.