



HEAD OFFICE
22 Park Drive
Dandenong VIC 3175

Phone: (03) 9768 4900
Fax (03) 9768 4999
www.unitex.com.au

NSW OFFICE
14 Artisan Road
Seven Hills NSW 2147

Phone: (02) 9838 0911
Fax (02) 9838 9555
www.unitex.com.au

RENDER WAREHOUSE

Phone: 1800 RENDER
www.render.com.au

14th August 2015

Unitex coating specification for the The Multipanel Wall System

Please find following the Unitex coating specifications over correctly installed Multipanel Wall System.(For installation guidelines please contact the system provider).

1. Ensure all dust, grime, grease, oils, laitance etc. have been removed and a dry, clean surface remains.
2. Apply Unitex Polymer Render (mixed with 5-10% cement) and imbed Unitex IM Mesh to entire surface (1-3mm as required). Allow to dry to 12% WME.
3. Apply Unitex Baseboard Render to a minimum thickness of 8mm. Allow to dry to 12% WME.
4. Apply one coat of Unitex Textured Finish to entire surface. Allow to dry to 12%WME.

All expansion, control and cosmetic joints are to be nominated by and are the responsibility of the builder – for only he and his engineer / architect etc. and base system provider can predict likely building and surface effect movement.

If you have any questions, please do not hesitate to call,

Yours Sincerely,

Luke Molloy
Sales Manager
Unitex